

POLYSPORT STUCCO 950

POLYURETHANE-BASED, TWO-COMPONENT, ELASTIC PORE SEALER

GENERAL CHARACTERISTICS

POLYSPORT STUCCO 950 is a polyurethane-based, two-component, solvent free, resinous paste designed for sealing of porous prefabricated subfloors of sports floorings such as **ISOPOL 854**.

- It is combined with flexible, polyurethane, self-leveling coating **POLYSPORT PU 951** and matt, polyurethane finish paint **POLYSPORT MAT 952** for the creation of a multilayer polyurethane floor especially designed for sport halls such as tennis, basketball, handball, volleyball and multipurpose halls.
- Applies easily with trowel, providing good filling properties.
- Highly flexible and elastic contributing in the athletic performance of the flooring
- Non shrinking, non flammable.

TECHNICAL DATA

Basis:	two-component polyurethane resin
Appearance:	liquid
Colors:	beige
Viscosity:	4500 ± 300 mPa•s at 23°C
Density:	1,425 ± 0,011 gr/cm ³
Mixing proportion (A:B):	100:18,6 by weight
Application time:	approx. 40 min at 23°C
Temperature for the application and drying of the material:	15 – 25°C

PREPARATION - APPLICATION

Applied only on dry surfaces, protected from arising humidity.

The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry** cleaning of the surface from dust and residues using vacuum cleaner and squeegees.
- Application of prefabricated sub-floor **ISOPOL 854** using **PU FLEX 140**.
- Caution must be taken so that temperature of the support surface as well as ambient air remains above 15°C during application and curing of the materials while relative humidity does not exceed 75%.
- Following, components A (resin) & B (hardener) of **POLYSPORT STUCCO 950** packed into separate containers in fixed weight proportions are mixed together using a low revolution mixer (300-600 rpm) for 1-2 min. Stirring of the mixture should be performed thoroughly near the sides and bottom of the container in order to achieve uniform dispersion of the hardener.
- The polyurethane mixture is poured on the floor and spread using trowel.

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr



- In case of high porosity subfloors a second layer of **POLYSPORT STUCCO 950** is advised after approx. 14 hours of the initial application depending ambient temperature.
- The next day, depending ambient temperature follows application of self-leveling coating **POLYSPORT PU 951** and the day after that finishing paint **POLYSPORT MAT 952**.

CONSUMPTION

- Approx. 0,5 kg/m² depending on the support surface and the porosity of floor covering.

APPLICATION TOOLS

Trowels. Tools should be cleaned with **PU SOLVENT 133** immediately after use.

PACKAGING

Supplied in set of 20 kg (two drums). Components A and B have the fixed weight proportion.

STORAGE

Six months in unopened containers in dry places with minimum temperature 5°C.

REMARKS

- Working time of **POLYSPORT STUCCO 950** decreases when ambient temperature rises.
- Prolonged storage of partially used containers containing **POLYSPORT STUCCO 950** must be avoided as contact with atmospheric moisture will result in skinning and clouding of the product.
- All surfaces should be thoroughly cleaned from dust and residues prior each application.
- Care should be taken that the porosity of prefabricated subfloor **ISOPOL 854** using **POLYSPORT STUCCO 950** is eliminated to avoid surface defects on the final surface of **POLYSPORT PU 951**.
- After hardening **POLYSPORT STUCCO 950** is completely safe for health.

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water. Flammable before application.

For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of POLAT S.A.

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr

