

ELASTOTURF 851

SPECIAL, ELASTIC, SELF-LEVELING COATING FOR INTERNAL AND EXTERNAL SPORT FIELDS

GENERAL CHARACTERISTICS

ELASTOTURF 851 is acrylic-based, elastic, self-leveling, colored, non-slip coating for external and internal sport fields, certified by the **INTERNATIONAL TENNIS FEDERATION (I.T.F.)**.

- Applied on asphalt and cement waterproofed surfaces following the application of **ELASTOSPORT 853** or **ELASTOCOAT 841** or **SUPER ELASTOCOAT 842**.
- It can be also combined with prefabricated shock-absorbent rolls in thickness 4-10mm or elastic sub floors **ELASTOCOAT 841** and **SUPER ELASTOCOAT 842**.
- Ideal for basketball, volleyball, handball and tennis external courts. Suitable for sports centers, schools, fitness centers, pavements, hallways.
- Applied easily, having low cost.
- Provides a safe, high quality game.
- Prevents high temperatures of the underlay.
- For interior surfaces, the smooth version of **ELASTOTURF** is used (**ELASTOTURF 851-S**). This should be combined with prefabricated shock-absorbent roll in thickness 4-10 mm or **ELASTOCOAT 841** or **SUPER ELASTOCOAT 842** and then 2,5 kg/m² of **ELASTOTURF 851-S** in order to seal the pores and plasticize the flooring.
- For the creation of lines in sport courts it is recommended the use of acrylic paint **ELASTOMARK 818** (former **AKRYLOEPOX**) in any desirable color.

TECHNICAL DATA

Basis:	one-component acrylic resin
Appearance:	viscous liquid
Colors:	Indian red, green, ochre, light and dark blue, light and dark grey and on request
Viscosity:	24000 ± 1250 mPa•s at 23°C
Density:	1,61 ± 0,01 gr/cm ³
Temperature for the application and drying of the material:	10 – 30°C
Walkability:	after 24 hours
Total Hardening:	5 days at 23°C
Adhesive strength:	1,20 ± 0,08 N/mm ²

PREPARATION - APPLICATION

Applied only on dry surfaces, protected from arising humidity and free of materials that might prevent bonding e.g. dust, loose particles, grease etc. The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry cleaning** of the surface from dust and residues with vacuum cleaner and squeegees.

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr



- Priming of the surface, except in case of using shock-absorbent rolls, with joining resin **RITIVEX 1102** or **AKRYLEX 165** for the proper adhesion of the sub-floor. Application of one or more layers until the surface is saturated. Avoid the creation of puddles of the material. Consumption: 150-250gr/m² in two layers, depending on the absorption of the underlay.

EXTERNAL SURFACES

- When the primer begins to dry (approximately 1 hour depending on the ambient temperature), follows the application of **ELASTOSPORT 853**, or **ELASTOCOAT 841**, or **SUPER ELASTOCOAT 842**, for sealing the pores of underlay.
- As soon as **ELASTOSPORT 853**, or **ELASTOCOAT 841**, or **SUPER ELASTOCOAT 842**, dries (48 hours at 23°C), follows the application of **ELASTOTURF 851**.
- Depending on the ambient temperature **ELASTOTURF 851** is diluted with 6-10% water, prior to application, in order to achieve better fluidity. It is applied in 2mm thickness, in three or five coatings depending on the desirable thickness. The next layer follows the other after the previous starts to dry.

INTERNAL SURFACES

- Application of the material on prefabricated shock-absorbent rolls in thickness 4-10mm or **ELASTOCOAT 841** or **SUPER ELASTOCOAT 842**, for sealing the pores of the underlay and plasticize the surface.
- Depending on the ambient temperature, **ELASTOTURF 851** is diluted with 6-10% water, prior to application, in order to achieve better fluidity. The next layer follows the other after the previous starts to dry.

CONSUMPTION

- 1 kg/m² as paint
- 1,6 kg/m²/mm

APPLICATION TOOLS

Nappy rolls, rubber spotty-like rolls of 1,7 and 2,5 mm, squeegees, brushes and generally any tool that can spread the material in a uniform thickness. Tools should be cleaned with **WATER** immediately after use.

PACKAGING

Supplied in drums of 25 kg.

STORAGE

One year in unopened containers in dry places with minimum temperature 5°C.

REMARKS

- In case of extremely rough and sharp cement or asphalt surfaces it is recommended grinding of the surface with a mosaic machine, sandblast or rotor machine before the application of **ELASTOSPORT 853**.
- **ELASTOTURF 851** should not be applied in more than 1,6 kg/m² per layer. In case of high temperature during summer, layers thicker than 1mm should be avoided because the material may crack due to the rapid evaporation of water. Lining thickness more than 1mm is achieved only by repeated layers.
- During summer, ideal time for the application of **ELASTOTURF (851)** is between 6:00-9:00 a.m. while in the winter, the minimum bearing temperature during application and drying should be 10°C.
- The freshly coated surface should be protected from high temperatures, wind, rain and frost for at least the first 24 hours.
- In case it gets damaged, it is simply repaired and recoated on the spot.

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.
For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of POLAT S.A.

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr

