

EPOFIX-H 207

(former EPOXY STUCCO TWO-COMPONENT)

EPOXY-BASED, TWO COMPONENT STUCCO FOR CRACKS, DAMAGES, FLOORING JOINTS

GENERAL CHARACTERISTICS

EPOFIX-H 207 is epoxy-based, two-component paste.

- Ideal for holes, cracks, damages on horizontal concrete surfaces, septic tanks, mosaics, industrial floorings, car repairing units, refrigeration rooms. Also for joint sealing on industrial floorings.
- Provides strong adhesion, high mechanical and chemical resistance to acid solutions, alkalis, oil, grease, wastes.
- Applied easily with stainless steel spatula, only on dry surfaces.
- Meets all health specifications and standards and multiplies the mechanical resistance in decayed places.

TECHNICAL DATA

Basis:	two-component epoxy resin
Appearance:	paste
Colors:	light brown and by desire for orders more than 300 kg
Viscosity (A+B):	132700 ± 2100 mPa•s at 23°C
Density (A+B):	1,660 ± 0,004 gr/cm ³
Mixing proportion (A:B):	50:50 by weight
Application time:	approx. 30 min at 23°C
Final strength:	after 7 days at 23°C
Compressive strength (A+B): (ASTM D 695)	90 N/mm ² , 7 days at 23°C
Flexural strength (A+B): (Din 1164)	45 N/mm ² , 7 days at 23°C
Temperature for the application and drying of the material:	10 - 35°C
Hardness according to SHORE D:	85 ± 2
Walkability:	after 2 days in thickness of 1 cm in 23°C
Adhesive strength:	3,82 ± 0,35 N/mm ² (breaking of concrete)

SUBSTRATE

Concrete quality: at least C20/25

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr



REQUIREMENTS

Age: at least 28 days
Moisture content: below 4%

PREPARATION - APPLICATION

Applied only on dry surfaces. Protected from arising humidity and free of materials that might prevent bonding e.g. dust, loose particles, grease etc. The success in the application depends on the right preparation of the underlay and use of the material.

- **Good, dry** cleaning of the surface from dust and residues with vacuum cleaner and squeegees.
- Priming of the surface with **POLEPOX-PR 824** (former EPOXY PRIMER). In case of troweled surfaces when there is a need for a penetrating material, it is suggested the application of the **POLEPOX-PR 824** (former EPOXY PRIMER), with dilution with 50% **EPOXY SOLVENT 132** for deeper penetration, in two layers. Then, application of another or more layers, with undiluted **POLEPOX-PR 824** (former EPOXY PRIMER), until the surface is saturated and a film is created. Consumption: 250-600 gr/m², depending on the absorption of the underlay.
- When primer starts to dry and while is still sticky (2-8 hours depending on the ambient temperature), follows the application of **EPOFIX-H 207**.
- Good mixing of components A (resin) & B (hardener) packed into separate containers in fixed weight proportions. Mixing should be performed using a 300-600 rpm mixer for 3-4 min until a uniform color is obtained. Stirring of the mixture should be performed thoroughly near the sides and bottom of the container in order to achieve uniform dispersion of the hardener.
- The epoxy paste is applied in the desired thickness using a stainless steel spatula.

CONSUMPTION

- 1,7 kg/m²/1mm.

APPLICATION TOOLS

Stainless steel spatula, trowel. Tools should be cleaned with **EPOXY SOLVENT 132** immediately after use.

PACKAGING

Supplied in packages of 10 kg (two drums). Components A and B have the fixed weight proportion.

STORAGE

One year in unopened containers in dry places with minimum temperature 5°C.

REMARKS

- Working time of **EPOFIX-H 207** decreases when ambient temperature rises.
- In case **POLEPOX-PR 824** (former EPOXY PRIMER)dries, surface must be locally roughed with the use of a mosaic machine or sandpaper in order to achieve the ideal adhesion for the material.
- After hardening, **EPOFIX-H 207** is completely safe for health.

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water. Flammable before application.

For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of POLAT S.A.

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr

