

POLEPOX FLOOR 837-F

(former FAST EPOXY HIGH RESISTANT FLOOR)

FAST-CURING, EPOXY-BASED, SELF-LEVELING, THREE COMPONENT FLOORING

GENERAL CHARACTERISTICS

POLEPOX FLOOR 837-F is epoxy-based, self-leveling, three-component **FAST CURING** flooring.

- Creates colored, easy-to-clean flooring without joints, not requiring maintenance and meeting **health standards**.
- Ideal for cases where **FAST WORK** is required.
- Resistant to acid solutions, alkalis, oil, grease, wastes.
- Prevents floorings from creating dust, strengthening their durability and resistance.
- Resistant to mechanical stresses, wearing from friction and chemical effects.
- It is ideal for covering floorings, mosaics, cement surfaces, decks, bio-cleanings, water baths, silos etc.
- Areas of application: food industries, car workshops, parking areas, bio-cleanings, production plants, hospitals for antibacterial use etc.

TECHNICAL DATA

Basis:	two-component epoxy resin, aggregates
Appearance:	viscous liquid
Colors:	available in 12 basic colors and on request from RAL color card for orders more than 300kg
Viscosity(A+B+C):	9900 ± 500 mPa•s at 23°C
Density (A+B+C):	1,601 ± 0,008 gr/cm ³
Bulk density (C):	1515 ± 5 gr/lit
Mixing proportion (A:B:C):	43:12:45 by weight
Granulometry (C):	160 µm - 500 µm
Application time:	approx. 20 min at 23°C
Final strength:	after 3 days at 23°C
Compressive strength (A+B+C): (ASTM D 695)	103 N/mm ² , 3 days at 23°C
Flexural strength (A+B+C): (Din 1164)	65 N/mm ² , 3 days at 23°C
Temperature & relative humidity for the application and drying of the material:	5 - 20°C, <50% RH

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr



Hardness according to SHORE D:	87 ± 3
Walkability:	less than 18 hours in thickness of 3mm at 23°C
Adhesive strength:	4,3 ± 0,4 N/mm ² (breaking of concrete)

SUBSTRATE REQUIREMENTS

Concrete quality:	at least C20/25
Age:	at least 28 days
Moisture content:	below 4%

PREPARATION - APPLICATION

Applied only on dry surfaces, protected from arising humidity and free of materials that might prevent bonding e.g. dust, loose particles, grease etc. The success in the application depends on the right preparation of the underlay and use of the material.

- Treatment of the surface with a mosaic machine, with sandblast or rotor machine, depending on the thickness of the final coating.
- **Good, dry** cleaning of the surface from dust and residues with vacuum cleaner and squeegees.
- Priming of the surface with **POLEPOX-PR 824** (former EPOXY PRIMER TWO COMPONENT). In case of troweled surfaces when there is a need for a penetrating material, it is suggested the application of the **POLEPOX-PR 824** (former EPOXY PRIMER TWO COMPONENT), with dilution with 50% **EPOXY SOLVENT 132** for deeper penetration, in two layers. Then, application of another or more layers, with undiluted **POLEPOX-PR 824** (former EPOXY PRIMER TWO COMPONENT), until the surface is saturated and a film is created. Consumption: 250-600 gr/m², depending on the absorption of the underlay.
- After hardening of the primer (2-12 hours depending on the ambient temperature) and within 24 hours, follows the application of **POLEPOX FLOOR 837-F**.
- Good mixing of components A (resin) & B (hardener) packed into separate containers in fixed weight proportions. Mixing should be performed using a low revolution mixer (300-600 rpm) for 1-2 min. Stirring of the mixture should be performed thoroughly near the sides and bottom of the container in order to achieve uniform dispersion of the hardener. Afterwards, the whole quantity of component C (quartz sand) is gradually added into the mixture under continuous stirring until a uniform epoxy mortar is formed.
- The epoxy mortar is poured on the floor and spread on the desired thickness using a notched trowel or special rolls.
- Following the application of the **POLEPOX FLOOR 837-F**, the self-leveling layer should be rolled using a special spiky-roller in order to release any possibly entrapped air and avoid the formation of bubbles.
- For the creation of a completely non-slip surface, it is recommended on a still fresh layer the dredging of dry, quartz sand with a particle size 0,1-0,4 mm or 0,4-0,8 mm or 0,8-1,25 mm depending on the desired anti-slipping effect. Consumption of quartz sand: approx. 4 kg/m². After hardening of **POLEPOX FLOOR 837-F**, any loose grains are being removed using a high suction vacuum cleaner. Finally a finishing layer of **POLEPOX COAT 834-F** (former FAST EPOXY TWO COMPONENT PAINT) is applied for the creation of an acid proof, easy to clean, non-slip surface. Consumption: 0,6-0,8 kg/m².

CONSUMPTION

- 1,6 Kg/m²/mm.
- 3,2 Kg/m²/2mm
- 4,3 Kg/m²/2,7mm

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr



**APPLICATION
TOOLS**

Rubber rolls of 1,7 and 2,5mm, notched trowel or spraying machine depending on the desired thickness. Tools should be cleaned with **EPOXY SOLVENT 132** immediately after use.

PACKAGING

Supplied in packages of 40 kg (two drums, one bag). Components A,B and C have the fixed weight proportion.

STORAGE

One year in unopened containers in dry places with minimum temperature 5°C.

REMARKS

- Working time of **POLEPOX FLOOR 837-F** decreases when ambient temperature rises.
 - In case old floors are going to be laid or a long period of time (12 hours for summer and 24 hours for winter) interferes between successive layers, the surface must be thoroughly cleaned and ground prior to application of a new layer.
 - After hardening, **POLEPOX FLOOR 837-F** is completely safe for health and meets all requirements for food industries.
-

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of POLAT S.A.

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr

