

POLRAPID 501

(former QUICK SETTING CEMENT)

GENERAL CHARACTERISTICS

Quick setting cement. The setting begins 8min after the addition of water and is completed after 15-30 min.

With addition 1-3 parts of aggregates, it creates concretes and mortars for repairs, stuccos of rapid setting, etc.

TECHNICAL DATA

Appearance: Powder form

Granulometry: 5-80

Temperature for the application and drying of the material: 5 - 35°C

APPLICATION

Mixed with 500-600gr water per kilo and is stirred up to complete homogenization.

The time of setting of cement depends on temperature, water added, and is tripled with the addition of aggregates

PACKAGING

Supplied in bags of 20 kg

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr

