

SVELTO MAZUN 201

POLYMERIC SPATULA STUCCO

FOR INTERNAL WALLS IN POWDER FORM

GENERAL CHARACTERISTICS

SVELTO MAZUN 201 is a ready to mix, acrylic stucco in powder form.

- It can be applied without any primer directly to the mortar, concrete etc in thickness up to 5 mm.
- Allows one layer after another and dries very quickly.
- Slides easily on the wall providing the maximum result, covers any abnormality, hole or crack in thickness 1-5mm. For thickness 5mm to 20mm, quartz sand or marble powder can be added, till the ratio 1:1. It creates a smooth, hard, ready to paint surface.
- It is not affected even if it will stay without painting, as final coating for interior surfaces.
- For even better adhesion, is suggested the addition 5-10% of **AKRYLEX 165 1101**.
- **ENVIRONMENTALLY FRIENDLY (DIN 55945)**.

TECHNICAL DATA

Colors: White

Temperature for the application and drying of the material: 5 - 35°C

PREPARATION - APPLICATION

- Good cleaning of the surface from dust, oils, grease, fungus or anything that can create adhesion problems.
- Mixing one kilogram of **SVELTO MAZUN (201)** with 500gr water and stirring well with mixer.
- The ready mix must stay in the drum for 2-10 min before its application. It allows the repeated coverings, the one immediately after the other, but **not** after the drying of the previous one.

CONSUMPTION

- 1-2 kg/m², depending on the type and roughness of the surface.

APPLICATION TOOLS

Spatula. Tools should be cleaned with **WATER** immediately after use.

PACKAGING

Supplied in bag of 20 kg.

STORAGE

One year in unopened containers in dry places with minimum temperature 5°C.

REMARKS

The fluidness of the mixture depends on the weather conditions (temperature), meaning more water during summer, less water during winter.

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr



ATTENTION : ADD THE POWDER INTO WATER AND NOT THE OPPOSITE.

CAUTION

The application must take place in well-aired places using protective gloves. Skin or eye contact must be avoided, otherwise wash carefully with soap and water.

For more information consult the material safety data sheet.

The information given here is true, represents our best knowledge and is based not only on laboratory work, but also on field experience. However, because of numerous factors affecting results we offer this information without any guarantee and no patent liability is assumed. For additional information or questions, contact the technical department of POLAT S.A.

Thessaloniki Office

10, 25th Martiou str., N. Efkarpia,
P.C.: 56429, Thessaloniki Greece
T.: (+30) 2310 680105, (+30) 2310 680382
F.: (+30) 2310 692866

e-mail: exports@polat.gr

Athens Office

109, Vouliagmenis Avenue, Glifada,
P.C.: 16674, Athens Greece
T.: (+30) 210 9647320
F.: (+30) 210 9646317

www.polat.gr

